

## NTA (nitrilotriacetic acid)-derivatized Poly(L-lysine)-g-poly(ethylene glycol): A Novel Polymeric Interface for Binding and Study of 6xHistidine-tagged Proteins

G.L.Zhen<sup>1</sup>, S.Zürcher<sup>1</sup>, D. Falconnet<sup>1</sup>, E. Kuennemann<sup>2</sup>, J. Vörös<sup>1</sup>, N. Spencer<sup>1</sup>, M. Textor<sup>1</sup>

<sup>1</sup> Laboratory for Surface Science and Technology, ETH Zurich, Zurich, Switzerland


<sup>2</sup> Institute for Molecular Biology and Biophysics, ETH Zurich, Zurich, Switzerland

**INTRODUCTION:** Interfaces are key elements in the design and fabrication of bioaffinity sensor chips with directed biological response. It has been reported that coating metal oxide surfaces with poly(L-lysine)-g-poly(ethylene glycol) (PLL-g-PEG) provides an attractive option for producing stable surfaces that are protein-resistant<sup>1</sup>. A novel NTA-functionalized PLL-g-PEG is presented that it can assemble on oxide surfaces as a monolayer, allows for the immobilization of proteins through NTA-Ni<sup>2+</sup>-histidine docking site chemistry.


**METHODS:** Graft copolymer PLL-g-PEG/PEG-NTA was synthesized with a fraction of the PEG chain terminus covalently functionalized with nitrilotriacetic acid (NTA) as a chelating ligand. The polymer was assembled from aqueous solution onto Nb<sub>2</sub>O<sub>5</sub> coated optical chips, followed by coordination of Ni<sup>2+</sup> to the surface-exposed NTA ligand. Subsequently, this sensing platform was used to specifically attach Histidine-tagged proteins, e.g., 6His-GFP (Green Fluorescent Protein) or enzymes, e.g., 6His-β-lactamase. Optical waveguide lightmode spectroscopy (OWLS) was used to monitor quantitatively and *in situ* for each step. Furthermore, the NTA-functionalized polymer was used to produce interactive micropatches in a non-interactive PLL-g-PEG background on Nb<sub>2</sub>O<sub>5</sub> coated surfaces by a novel approach termed molecular assembly patterning by lift-off (MAPL)<sup>2</sup>. The quality of the 6His-GFP patterns was evaluated by confocal laser scanning microscopy (CLSM).

**RESULTS:** OWLS studies of 6His-GFP bound to NTA-functionalized polymer modified surfaces proved that the binding of 6xHis-tagged proteins was stable and required the presence of Ni<sup>2+</sup> attached to the NTA functionalities. The proteins could be fully removed by exposing the surface to imidazole or EDTA. Non-specific adsorptions of 6His-GFP and 6His-β-lactamase were below 2 ng/cm<sup>2</sup>. Binding and desorption of 6xHis-tagged proteins was repeated in several cycles demonstrating the excellent regeneration capacity of the novel platform (Fig. 1). Fluorescence microscopy measurement proved that the patterning was successful and that surface-

immobilized 6His-GFP was in an active conformation (Fig. 2).



**Fig. 1:** Adsorbed mass measured by OWLS of the sequential adsorption of PLL-g-PEG/PEG-NTA, Ni<sup>2+</sup>, 6His-GFP and 6xHis-β-lactamase. Quantitative regeneration of the surface was achieved by adding either EDTA, which removes Ni<sup>2+</sup> or imidazole, which removes only the His-tagged protein, but not Ni<sup>2+</sup>.



**Fig. 2:** Pattern of 6His-GFP on Nb<sub>2</sub>O<sub>5</sub> analyzed by CLSM. The scale bar represents 60 μm. (A) 6His-GFP immobilized on MAPL patterned substrate after charging with Ni<sup>2+</sup>. (B) As A, rinsed with imidazole removing 6His-GFP. (C) As B, reloaded with 6His-GFP.

**DISCUSSION & CONCLUSIONS:** We have demonstrated that the novel PLL-g-PEG/PEG-NTA polymeric interface is a promising approach for the binding of 6xHis-tagged proteins in an oriented manner with active conformation. Furthermore, the combination of the MAPL patterning technique with the PLL-g-PEG/PEG-NTA system is considered to be a promising technique for the production of functional microarrays in the area of genomics and proteomics.

### REFERENCES:

- (1) Kenausis, G. L.; Voros, J.; Elbert, D. L.; Huang, N. P.; Hofer, R.; Ruiz-Taylor, L.; Textor, M.; Hubbell, J. A.; Spencer, N. D. *Journal of Physical Chemistry B* 2000, 104, 3298-3309.
- (2) Falconnet, D.; Koenig, A.; Assi, T.; Textor, M. *Advanced Functional Materials* 2004, 14, 749-756.